

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
15 July 2004 (15.07.2004)

PCT

(10) International Publication Number  
**WO 2004/058876 A1**

(51) International Patent Classification<sup>7</sup>: C08L 23/04,  
C08F 297/08

Rainer [DE/DE]; Augustaanlage 26, 68165 Mannheim  
(DE).

(21) International Application Number:  
PCT/EP2003/013867

(22) International Filing Date: 6 December 2003 (06.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,  
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,  
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(30) Priority Data:  
102 61 066.5 24 December 2002 (24.12.2002) DE  
60/445,163 5 February 2003 (05.02.2003) US

(84) Designated States (*regional*): ARIPO patent (BW, GH,  
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,  
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): BASELL  
POLYOLEFINE GMBH [DE/DE]; Brühler Strasse,  
50389 Wesseling (DE).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): BERTHOLD,  
Joachim [DE/DE]; Am Flachsland 54, 65779 Kelkheim  
(DE). BÖHM, Ludwig [DE/DE]; Leonhardstrasse 36,  
65795 Hattersheim (DE). KRÜMPPEL, Peter [DE/DE];  
Hopfenstrasse 6, 65520 Bad Camberg (DE). MANTEL,

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: POLYETHYLENE BLOW MOULDING COMPOSITION FOR PRODUCING JERRY CANS

(57) Abstract: The invention relates to a polyethylene composition with multimodal molecular mass distribution, which is particularly suitable for the blow moulding of canisters having a volume in the range of from 2 to 20 dm<sup>3</sup> (l). The composition has a density in the range from 0.950 to 0.958 g/cm<sup>3</sup> at 23 °C and an MFR<sub>190/5</sub> in the range of from 0.30 to 0.50 dg/min. It comprises from 40 to 50 % by weight of a low-molecular-mass ethylene homopolymer A, from 25 to 35 % by weight of a high-molecular-mass copolymer B made from ethylene and from another olefin having from 4 to 8 carbon atoms, and from 24 to 28 % by weight of an ultrahigh-molecular-mass ethylene copolymer C.

WO 2004/058876 A1

Title: Polyethylene blow moulding composition for producing jerry cans

The present invention relates to a polyethylene composition with multimodal molecular mass distribution, which is particularly suitable for blow moulding of canisters with a capacity in the range from 2 to 20 dm<sup>3</sup> (l) (jerry cans), and to a process for preparing this polyethylene composition in the presence of a catalytic system composed of a Ziegler catalyst and a co-catalyst, by way of a multistage reaction process composed of successive slurry polymerizations. The invention further relates to the canisters produced from the molding composition by blow moulding.

Polyethylene is widely used for producing blow mouldings of all types requiring a material with particularly high mechanical strength, high corrosion resistance, and absolutely reliable long-term stability. Another particular advantage of polyethylene is that it also has good chemical resistance and is intrinsically a lightweight material.

EP-A-603,935 has previously described a blow moulding composition based on polyethylene having a bimodal molecular mass distribution, which is suitable for the production of mouldings with good mechanical properties.

US-A 5,338,589 describes a material with even broader molecular mass distribution, prepared using a high-mileage catalyst known from WO 91/18934, in which the magnesium alcoholate is used in the form of a gel-like suspension. Surprisingly, it has been found that the use of this material in mouldings, in particular in pipes, permits simultaneous improvement in properties which are usually contrary correlated in semicrystalline thermoplastics, these being stiffness and creep on the one hand and stress-crack resistance and toughness on the other hand.

However, the known bimodal products in particular have relatively low melt strength during processing. This means that the extruded parison frequently break in the molten state, making the extrusion process unacceptably sensitive to processing. In addition, especially when thick-walled containers are being  
5 produced, the wall thickness is found to be non-uniform, due to flow of the melt from upper regions into lower regions.

It is an objective of the present invention, therefore, to develop a polyethylene composition for blow moulding which can give a further improvement over all of  
10 the known materials in processing by blow moulding to canisters. In particular, the high melt strength of the moulding composition permits to run an extrusion process without parison disruption over a long time period, and the precisely adjusted swell ratio index of the composition permits optimization of wall-thickness control.

15 We have found that this objective is achieved by a composition as mentioned at the outset, the characterizing features of which are that it comprises from 40 to 50 % by weight of a low-molecular-mass ethylene homopolymer A, from 25 to 35 % by weight of a high-molecular-mass copolymer B made from ethylene and  
20 from another 1-olefin having from 4 to 8 carbon atoms, and from 24 to 28 % by weight of an ultrahigh-molecular-mass ethylene-1-olefin copolymer C, where all of the percentage data are based on the total weight of the composition.

The invention also relates to a process for preparing this composition in a  
25 cascaded slurry polymerization and to a process for producing, from this composition, canisters with a capacity in the range from 2 to 20 dm<sup>3</sup> (l) and with quite excellent mechanical strength properties.

The polyethylene composition of the invention has a density in the range from  
30 0.950 to 0.958 g/cm<sup>3</sup> at 23 °C, and a broad trimodal molecular mass distribution. The high-molecular-mass copolymer B contains only small

proportions of other olefin monomer units having from 4 to 8 carbon atoms, namely from 0.2 to 0.5 % by weight. Examples of these comonomers are 1-butene, 1-pentene, 1-hexene, 1-octene, or 4-methyl-1-pentene. The ultrahigh-molecular-mass ethylene homo- or copolymer C also contains an amount in the range from 1 to 2 % by weight of one or more of the above mentioned comonomers.

The composition of the invention has a melt flow index ISO 1133 in the range of from 0.30 to 0.50 dg/min, expressed in terms of MFR<sub>190/5</sub>, and a viscosity number VN<sub>tot</sub> in the range of from 330 to 380 cm<sup>3</sup>/g, in particular from 340 to 370 cm<sup>3</sup>/g, measured according to ISO/R 1191 in decalin at 135 °C.

The trimodality is a measure of the position of the centers of gravity of the three individual molecular mass distributions, and can be described with the aid of the viscosity number VN to ISO/R 1191 of the polymers formed in the successive polymerization stages. The relevant band widths for the polymers formed in each of the stages of the reaction are therefore as follows:

The viscosity number VN<sub>1</sub> measured on the polymer after the first polymerization stage is identical with the viscosity number VN<sub>A</sub> of the low-molecular-mass polyethylene A and according to the invention is in the range from 60 to 80 cm<sup>3</sup>/g.

The viscosity number VN<sub>2</sub> measured on the polymer after the second polymerization stage is not equal to VN<sub>B</sub> of the high-molecular-mass polyethylene B formed in the second polymerization stage, which can only be determined by calculation, but represents the viscosity number of the mixture of polymer A and polymer B. According to the invention, VN<sub>2</sub> is in the range from 160 to 200 cm<sup>3</sup>/g.

The viscosity number  $VN_3$  measured on the polymer after the third polymerization stage is not equal to  $VN_C$  of the ultra-high-molecular-mass copolymer C formed in the third polymerization stage, which can only be determined by calculation, but represents the viscosity number of the mixture of polymer A, polymer B, and polymer C. According to the invention,  $VN_3$  is in the range of from 330 to 380  $\text{cm}^3/\text{g}$ , in particular from 350 to 370  $\text{cm}^3/\text{g}$ .

The polyethylene is obtained by polymerizing the monomers in slurry in the range of from 70 to 90 °C, preferably from 80 to 90 °C, at a pressure in the range of from 0.15 to 1 MPa, and in the presence of a high-mileage Ziegler catalyst composed of a transition metal compound and of an organoaluminum compound such as triethylaluminum, triisobutylaluminum, alkylaluminum-chlorides or alkylaluminumhydrides. The polymerization is conducted in three stages, i.e. in three stages arranged in series, each molecular mass being regulated with the aid of hydrogen feed.

The polyethylene composition of the invention may comprise other additives alongside the polyethylene. Examples of these additives are heat stabilizers, antioxidants, UV absorbers, light stabilizers, metal deactivators, compounds which destroy peroxide, and basic costabilizers in amounts of from 0 to 10 % by weight, preferably from 0 to 5 % by weight, and also fillers, reinforcing agents, plasticizers, lubricants, emulsifiers, pigments, optical brighteners, flame retardants, antistats, blowing agents, or a combination of these, in total amounts of from 0 to 50 % by weight, based on the total weight of the mixture.

The composition of the invention is particularly suitable for the blow moulding process to produce canisters, by first plastifying the polyethylene composition in an extruder in the range from 200 to 250 °C and then extruding it through a die into a mould, where it is cooled and solidified.

The composition of the invention gives particularly good processing behavior in the blow moulding process to give canisters because it has a swell ratio index in the range of from 130 to 145 %, and the canisters produced therewith have particularly high mechanical strength because the moulding composition of the invention has a notched impact strength (ISO) in the range from 14 to 17 kJ/m<sup>2</sup>.  
The stress-crack resistance (FNCT) is in the range from 150 to 220 h.

The notched impact strength<sub>ISO</sub> is measured according to ISO 179-1/1eA / DIN 53453 at 23 °C. The size of the specimen is 10 x 4 x 80 mm, and a V notch is inserted using an angle of 45°, with a depth of 2 mm and with a notch base radius of 0.25 mm.

The stress-crack resistance of the molding composition of the invention is determined by an internal test method and is given in h. This laboratory method is described by M. Fleißner in Kunststoffe 77 (1987), pp. 45 et seq., and corresponds to ISO/FDIS 16770, which has since come into force. In ethylene glycol as stress-crack-promoting medium at 80°C with a tensile stress of 3.5 MPa, the time to failure is shortened due to the shortening of the stress-initiation time by the notch (1.6 mm/razorblade). The specimens are produced by sawing out three specimens of dimensions 10 x 10 x 90 mm from a pressed plaque of thickness 10 mm. These specimens are provided with a central notch, using a razorblade in a notching device specifically manufactured for the purpose (see Figure 5 in the publication). The notch depth is 1.6 mm.

## Example 1

Ethylene was polymerized in a continuous process in three reactors arranged in series. An amount of 1.3 Mol/h related to the titanium compound of a Ziegler catalyst prepared as specified in WO 91/18934, Example 2, and having the operative number 2.2 in the WO, was fed into the first reactor together with 2.7 Mol/h triethylaluminum, as well as sufficient amounts of diluent (hexane), ethylene, and hydrogen. The amount of ethylene (= 6.75 t/h) and the amount of hydrogen (= 7.3 kg/h) were adjusted so that the percentage proportion of ethylene and of hydrogen measured in the gas phase of the first reactor were 18 % by volume and 70 % by volume, respectively, and the rest was a mix of nitrogen and vaporized diluent.

The polymerization in the first reactor was carried out at 84 °C.

The slurry from the first reactor was then transferred into a second reactor, in which the percentage proportion of hydrogen in the gas phase had been reduced between 10 to 12 % by volume, and an amount of 16.6 kg/h of 1-butene was added to this reactor alongside 4.35 t/h of ethylene. The amount of hydrogen was reduced by way of intermediate H<sub>2</sub> depressurization. 70 % by volume of ethylene, 10.5 % by volume of hydrogen, and 1.1 % by volume of 1-butene were measured in the gas phase of the second reactor, the rest being a mix of nitrogen and vaporized diluent.

The polymerization in the second reactor was carried out at 82 °C.

The slurry from the second reactor was transferred to the third reactor using further intermediate H<sub>2</sub> depressurization to adjust the amount of hydrogen to 0.5 % by volume in the gas phase of the third reactor.

An amount of 67 kg/h of 1-butene was added to the third reactor alongside an amount of 3.90 t/h of ethylene. A percentage proportion of from 85 % by volume of ethylene, 0.5 % by volume of hydrogen, and 2.2 % by volume of 1-butene was measured in the gas phase of the third reactor, the rest being a mix of nitrogen and vaporized diluent.

The polymerization in the third reactor was carried out at 80 °C.

The long-term polymerization catalyst activity required for the cascaded process described above was provided by a specifically developed Ziegler catalyst as described in the WO mentioned at the outset. A measure of the usefulness of this catalyst is its extremely high hydrogen sensitivity and its uniformly high activity over a long time period of between 1 to 8 h.

The diluent was removed from the polymer slurry leaving the third reactor, and the material was dried and then pelletized.

Table 1 shown below gives the viscosity numbers and quantitative proportions  $w_A$ ,  $w_B$ , and  $w_C$  of polymer A, B, and C for the polyethylene moulding composition prepared in Example 1.

Table 1

Example No.	1
density [g/cm <sup>3</sup> ]	0.954
MFR <sub>190/5</sub> [dg/min]	0.40
$w_A$ [% by weight]	45
$w_B$ [% by weight]	29

$W_c$ [% by weight]	26
$VN_1$ [ $\text{cm}^3/\text{g}$ ]	70
$VN_2$ [ $\text{cm}^3/\text{g}$ ]	180
$VN_{\text{tot}}$ [ $\text{cm}^3/\text{g}$ ]	360
SR [%]	135
FNCT [h]	170
$NIS_{\text{ISO}}$ [ $\text{kJ}/\text{m}^2$ ]	16

The abbreviations for physical properties in Table 1 have the following meanings:

- 5    -    SR (= swell ratio) in [%] measured in a high-pressure capillary rheometer at a shear rate of  $1440 \text{ s}^{-1}$ , in a 2/2 round-section die with conical inlet (angle =  $15^\circ$ ) at  $190^\circ\text{C}$ .
- FNCT = stress-crack resistance (Full Notch Creep Test) tested using the  
10    internal test method of M. Fleißner, in [h],
- $NIS_{\text{ISO}}$  = notched impact strength measured to ISO 179-1/1eA / DIN 53453 in [ $\text{kJ}/\text{m}^2$ ] at  $23^\circ\text{C}$ .

We claim

5

1. A polyethylene moulding composition with multimodal molecular mass distribution, which has a density in the range of from 0.950 to 0.958 g/cm<sup>3</sup> at 23 °C and an MFR<sub>190/5</sub> in the range of from 0.30 to 0.50 dg/min, and which comprises from 40 to 50 % by weight of a low-molecular-mass ethylene homopolymer A, from 25 to 35 % by weight of a high-molecular-mass copolymer B made from ethylene and from another 1-olefin having from 4 to 8 carbon atoms, and from 24 to 28 % by weight of an ultrahigh-molecular-mass ethylene copolymer C, wherein all of the percentage data are based on the total weight of the moulding composition.

15

2. A polyethylene composition as claimed in claim 1, wherein the high-molecular-mass copolymer B contains small proportions of from 0.2 to 0.5 % by weight of co-monomer having from 4 to 8 carbon atoms, based on the weight of copolymer B, and wherein the ultrahigh-molecular-mass ethylene copolymer C contains an amount in the range from 1 to 2 % by weight of comonomers, based on the weight of copolymer C.

20

3. A polyethylene composition as claimed in claim 1 or 2, which, as co-monomer, contains 1-butene, 1-pentene, 1-hexene, 1-octene, 4-methyl-1-pentene, or a mixture of these.

25

4. A polyethylene composition as claimed in one or more of claims 1 to 3, which has a viscosity number VN<sub>tot</sub> of from 330 to 380 cm<sup>3</sup>/g, preferably from 340 to 370 cm<sup>3</sup>/g, measured to ISO/R 1191 in decalin at 135 °C.

30

5. A polyethylene composition as claimed in one or more of claims 1 to 4, which has a swell ratio in the range of from 130 to 145 %, and a notched impact strength (ISO) in the range of from 14 to 17 kJ/m<sup>2</sup>, and a stress-crack resistance (FNCT) in the range of from 150 to 220 h.
- 5
6. A process for producing a polyethylene composition as claimed in one or more of claims 1 to 5, in which the monomers are polymerized in suspension at a temperature in the range of from 20 to 120 °C, at a pressure in the range of from 0.15 to 1 MPa, and in the presence of a
- 10 high-mileage Ziegler catalyst composed of a transition metal compound and of an organoaluminum compound, which comprises conducting polymerization in three stages, where the molecular mass of the polyethylene prepared in each stage is regulated with the aid of hydrogen.
- 15 7. A process as claimed in claim 6, wherein the hydrogen concentration in the first polymerization stage is adjusted so that the viscosity number VN<sub>1</sub> of the low-molecular-mass polyethylene A is in the range from 60 to 80 cm<sup>3</sup>/g.
- 20 8. A process as claimed in claim 6 or 7, wherein the hydrogen concentration in the second polymerization stage is adjusted so that the viscosity number VN<sub>2</sub> of the mixture of polymer A and polymer B is in the range from 160 to 200 cm<sup>3</sup>/g.
- 25 9. A process as claimed in any of claims 6 to 8, wherein the hydrogen concentration in the third polymerization stage is adjusted so that the viscosity number VN<sub>3</sub> of the mixture of polymer A, polymer B, and polymer C is in the range of from 330 to 380 cm<sup>3</sup>/g, in particular of from 340 to 370 cm<sup>3</sup>/g.

10. The use of a polyethylene composition as claimed in one or more of  
claims 1 to 5 for producing canisters with a capacity in the range from 2 to  
20 dm<sup>3</sup> (l), where the polyethylene composition is first plasticized in an  
extruder in the range from 200 to 250 °C and is then extruded through a  
5 die into a mould, where it is first blown up and then cooled and solidified.

\* \* \* \* \*

## INTERNATIONAL SEARCH REPORT

PCT/EP 03/13867

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L23/04 C08F297/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 199 45 980 A (ELENAC GMBH) 29 March 2001 (2001-03-29) the whole document	1-10
X	US 4 536 550 A (IKEGAMI TADASHI ET AL) 20 August 1985 (1985-08-20) the whole document	1-10
X	US 4 336 352 A (SAKURAI HISAYA ET AL) 22 June 1982 (1982-06-22) the whole document	1-10
A	US 6 242 548 B1 (KASPAR HARALD ET AL) 5 June 2001 (2001-06-05) the whole document	1-10
	-/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*Z\* document member of the same patent family

Date of the actual completion of the international search

25 March 2004

Date of mailing of the international search report

31/03/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Van Golde, L

## INTERNATIONAL SEARCH REPORT

PCT/EP 03/13867

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 603 935 A (SOLVAY) 29 June 1994 (1994-06-29) cited in the application the whole document -----	1-10

## INTERNATIONAL SEARCH REPORT

PCT/EP 03/13867

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 19945980	A	29-03-2001	DE 19945980 A1	29-03-2001
			AT 244264 T	15-07-2003
			AU 769434 B2	29-01-2004
			AU 7001700 A	30-04-2001
			BR 0014232 A	04-06-2002
			CA 2387708 A1	05-04-2001
			CN 1376170 T	23-10-2002
			DE 50002772 D1	07-08-2003
			WO 0123446 A1	05-04-2001
			EP 1228101 A1	07-08-2002
			JP 2003510429 T	18-03-2003
US 4536550	A	20-08-1985	JP 1012777 B	02-03-1989
			JP 1612249 C	30-07-1991
			JP 59196345 A	07-11-1984
			JP 1012778 B	02-03-1989
			JP 1612250 C	30-07-1991
			JP 59196346 A	07-11-1984
			JP 60036546 A	25-02-1985
			JP 1012781 B	02-03-1989
			JP 1612255 C	30-07-1991
			JP 60036547 A	25-02-1985
			CA 1218181 A1	17-02-1987
			DE 3470168 D1	05-05-1988
			EP 0129312 A1	27-12-1984
US 4336352	A	22-06-1982	JP 1282819 C	27-09-1985
			JP 56032506 A	02-04-1981
			JP 59010724 B	10-03-1984
			BE 884866 A1	16-12-1980
			BR 8005307 A	04-03-1981
			CA 1138148 A1	21-12-1982
			DE 3031540 A1	09-04-1981
			FR 2463791 A1	27-02-1981
			GB 2056996 A , B	25-03-1981
			IT 1193551 B	08-07-1988
			NL 8004745 A , C	26-02-1981
US 6242548	B1	05-06-2001	AU 6044399 A	05-12-2000
			CA 2372222 A1	23-11-2000
			EP 1185583 A1	13-03-2002
			WO 0069969 A1	23-11-2000
EP 0603935	A	29-06-1994	BE 1006439 A3	30-08-1994
			AT 191724 T	15-04-2000
			AU 670976 B2	08-08-1996
			AU 5249693 A	30-06-1994
			BR 9305106 A	28-06-1994
			CZ 9302853 A3	13-07-1994
			DE 69328345 D1	18-05-2000
			DE 69328345 T2	07-12-2000
			EP 1364971 A2	26-11-2003
			EP 0603935 A1	29-06-1994
			EP 0940411 A2	08-09-1999
			ES 2147192 T3	01-09-2000
			FI 935772 A	22-06-1994
			GR 3033922 T3	30-11-2000
			HU 66491 A2	28-11-1994

## INTERNATIONAL SEARCH REPORT

PCT/EP 03/13867

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0603935	A	NO 934729 A	22-06-1994
		PL 301589 A1	27-06-1994
		PT 603935 T	31-10-2000
		US 6344522 B1	05-02-2002
		US 6407185 B1	18-06-2002
		US 6136924 A	24-10-2000
		ZA 9309588 A	11-08-1994
<hr/>			